

SPECIFICATION ON THE PRODUCTS OF ORSHA LINEN MILL

DESCRIPTION	ARTICLE		WIDTH IN CMS	COMPOSITION OF FABRIC, %				COUNT OF YARN (METRIC)		DENSITY PER 10 CMS		WEIGHT OF 1 SQ. MTR. IN GRMS.
	OLD	NEW		LINEN	COTT.	PE	VISC.	WARP	WEFT	WARP	WEFT	
FABRIC SEMI-BLEACHED	OBR.296	02C129- III/PII	150-2	100	-	-	-	33,3 LINEN	33,3 LINEN	158+-3	132+-4	85 - 6
FABRIC SEMI-NATURAL	OBR. 0232	14C351- III/PII	150-2	100	-	-	-	33,3 LINEN	33,3 LINEN	158+-3	134+-4	90 - 6
FABRIC SEMI-BLEACHED	OBR.061	06C346- III/PII	150-2	100	-	-	-	33,3 LINEN	33,3 LINEN	180+-4	164+-5	105 - 7
FABRIC SEMI-BLEACHED	OBR.0167	12C30- III/PII	150-2	100	-	-	-	33,3 LINEN	26,3 LINEN	180+-4	166+-5	115 - 8
FABRIC NATURAL	OBR.1566	09C348-III/PII	145-2	100	-	-	-	11,5 LINEN	11,5 LINEN	68+-2	73+-2	120 - 8
FABRIC SEMI-BLEACHED	OBR.1567	09C343-III/PII	145-2	100	-	-	-	11,5 LINEN	11,5 LINEN	68+-2	73+-2	120 - 8
FABRIC COLOR WOVEN	OBR.020	03C68-III/PII /PII+X+Y	150-2	100	-	-	-	33,3 LINEN	33,3 LINEN	226+-5	178+-5	125 - 8
FABRIC SEMI-BLEACHED	OBR.78	2C64- III/PII	150-2	100	-	-	-	33,3 LINEN	33,3 LINEN	226+-5	174+-5	125 - 9
FABRIC SEMI-BLEACHED	OBR.057	06C251- III/PII	160-2,5	100	-	-	-	33,3 LINEN	33,3 LINEN	226+-5	174+-5	125 - 9
FABRIC NATURAL	OBR.166	6C11- III/PII	150-2	100	-	-	-	33,3 LINEN	33,3 LINEN	226+-5	174+-5	125 - 9
FABRIC SEMI-NATURAL	OBR.126	3C136- III/PII	150-2	100	-	-	-	33,3 LINEN	33,3 LINEN	226+-5	174+-5	130 - 9
FABRIC SEMI-BLEACHED	OBR.840	00C6- III/PII.1	150-2	100	-	-	-	26,3 LINEN	26,3 LINEN	199+-4	150+-5	140 - 10
FABRIC SEMI-BLEACHED	OBR.040	05C212- III/PII	150-2	100	-	-	-	26,3 LINEN	26,3 LINEN	199+-4	180+-6	150 - 11

Fax: (372) 6839384
 Phone: (372) 6839383
 www.belinor.eu
 E-mail: info@belinor.eu

Minimum lot for dyeing fabrics in 1 color is 500-700 meters.
 The linen yarns Nm 9,52; 11,5; 17,2 are combed yarns.

SPECIFICATION ON THE PRODUCTS OF ORSHA LINEN MILL

DESCRIPTION	ARTICLE		WIDTH IN CMS	COMPOSITION OF FABRIC, %				COUNT OF YARN (METRIC)		DENSITY PER 10 CMS		WEIGHT OF 1 SQ. MTR. IN GRMS.
	OLD	NEW		LINEN	COTT.	PE	VISC.	WARP	WEFT	WARP	WEFT	
FABRIC SEMI-BLEACHED	OBR.0213	14C74-IIP	250-3	100	-	-	-	26,3 LINEN	26,3 LINEN	199+-4	178+-6	135 - 11
FABRIC NATURAL	OBR.051	05C336- IIP/PIH	150-2	100	-	-	-	26,3 LINEN	26,3 LINEN	199+-4	184+-6	150 - 11
FABRIC SEMI-NATURAL	OBR.052	06C112- IIP/PIH	150-2	100	-	-	-	26,3 LINEN	26,3 LINEN	199+-4	182+-6	150 - 11
FABRIC SEMI-BLEACHED	OBR.0191	13C478- IIP	260-3	100	-	-	-	23,8 LINEN	23,8 LINEN	180+-4	178+-5	150 - 11
FABRIC SEMI-NATURAL	OBR.0268	15C444- IIP	260-3	100	-	-	-	23,8 LINEN	23,8 LINEN	180+-4	184+-6	160 - 11
FABRIC SEMI-BLEACHED	OBR.0114	08C341- IIP/PIH	150-2	100	-	-	-	23,8 LINEN	23,8 LINEN	193+-4	194+-6	170 - 12
FABRIC SEMI-BLEACHED	OBR.1735	10C607- IIP/PIH	150-2	100	-	-	-	20,0 LINEN	20,0 LINEN	167+-3	164+-5	175 - 12
FABRIC SEMI-BLEACHED	OBR.0258	15C417-IIP	150-2	100	-	-	-	20,0 LINEN	20,0 LINEN	158+-3	126+-4	140 - 10
FABRIC SEMI-BLEACHED	OBR.1520	08C415-IIP	150-2	100	-	-	-	9,09 LINEN	9,52 LINEN	87+-2	80+-2	180 - 13
FABRIC SEMI-BLEACHED	OBR.1301	06C243- IIP/PIH	160-2,5	100	-	-	-	17,9 LINEN	17,9 LINEN	174+-4	138+-4	180 - 13
FABRIC SEMI-BLEACHED	OBR.491	4C33- IIP/PIH	150-2	100	-	-	-	17,9 LINEN	17,9 LINEN	176+-4	142+-4	185 - 13
FABRIC SEMI-BLEACHED	OBR.0243	15C28- IIP	260-3	100	-	-	-	17,9 LINEN	17,9 LINEN	180+-4	143+-4	185 - 13

Fax: (372) 6839384
 Phone: (372) 6839383
 www.belinor.eu
 E-mail: info@belinor.eu

Minimum lot for dyeing fabrics in 1 color is 500-700 meters.
 The linen yarns Nm 9,52; 11,5; 17,2 are combed yarns.

SPECIFICATION ON THE PRODUCTS OF ORSHA LINEN MILL

DESCRIPTION	ARTICLE		WIDTH IN CMS	COMPOSITION OF FABRIC, %				COUNT OF YARN (METRIC)		DENSITY PER 10 CMS		WEIGHT OF 1 SQ. MTR. IN GRMS.
	OLD	NEW		LINEN	COTT.	PE	VISC.	WARP	WEFT	WARP	WEFT	
FABRIC SEMI-NATURAL	OBR.0261	15C426-IIP	260-3	100	-	-	-	17,9 LINEN	17,9 LINEN	180+-4	146+-4	195 - 13
FABRIC NATURAL	OBR.1072	02C135-IIP/PIH	155-3	100	-	-	-	17,9 LINEN	17,9 LINEN	172+-4	140+-4	185 - 13
FABRIC SEMI-NATURAL	OBR.831	9C93-IIP/PIH	150-2	100	-	-	-	17,9 LINEN	17,9 LINEN	176+-4	142+-4	190 - 13
FABRIC NATURAL	OBR.1209	05C221-IIP	150-2	100	-	-	-	9,09 LINEN	9,09 LINEN	83+-2	88+-3	195 - 14
FABRIC NATURAL	OBR.789	8C215-IIP	150-2	100	-	-	-	12,1 LINEN	12,1 LINEN	143+-3	106+-3	215 - 15
FABRIC SEMI-BLEACHED	OBR.1561	09C209-IIP	150-2	100	-	-	-	14,7 LINEN	14,7 LINEN	174+-4	133+-4	215 - 15
FABRIC SEMI-NATURAL	OBR.1133	04C25-IIP	150-2	100	-	-	-	12,1 LINEN	12,1 LINEN	143+-3	108+-3	215 - 15
FABRIC SEMI-BLEACHED	OBR.1025	03C42-IIP	150-2	100	-	-	-	12,1 LINEN	12,1 LINEN	156+-3	112+-3	220 - 15
FABRIC SEMI-BLEACHED	OBR.1635	10C178-IIP	180-3	100	-	-	-	11,5 LINEN	11,5 LINEN	156+-3	116+-3	240 - 17
FABRIC SEMI-NATURAL	OBR.1099	03C36-IIP	150-2	100	-	-	-	11,5 LINEN	12,1 LINEN	156+-3	112+-3	240 - 17
FABRIC NATURAL	OBR.1041	02C77-IIP	150-2	100	-	-	-	12,1 LINEN	12,1 LINEN	160+-3	112+-3	240 - 17
FABRIC NATURAL	OBR.1588	09C469-IIP	155-2,5	100	-	-	-	11,5 LINEN	11,5 LINEN	151+-3	112+-3	245 - 17
FABRIC SEMI-BLEACHED	OBR.1542	09C52-IIP	150-2	100	-	-	-	11,5 LINEN	11,5 LINEN	156+-3	118+-2	245 - 17

Fax: (372) 6839384
 Phone: (372) 6839383
 www.belinor.eu
 E-mail: info@belinor.eu

Minimum lot for dyeing fabrics in 1 color is 500-700 meters.
 The linen yarns Nm 9,52; 11,5; 17,2 are combed yarns.

SPECIFICATION ON THE PRODUCTS OF ORSHA LINEN MILL

DESCRIPTION	ARTICLE		WIDTH IN CMS	COMPOSITION OF FABRIC, %				COUNT OF YARN (METRIC)		DENSITY PER 10 CMS		WEIGHT OF 1 SQ. MTR. IN GRMS.
	OLD	NEW		LINEN	COTT.	PE	VISC.	WARP	WEFT	WARP	WEFT	
FABRIC SEMI-NATURAL	OBR.1471/1	08C232-IIP/1	155-2,5	100	-	-	-	11,5 LINEN	11,5 LINEN	156+-3	110+-3	245 - 17
FABRIC SEMI-NATURAL	OBR.2042	15C261-IIP	260-3	100	-	-	-	11,5 LINEN	11,5 LINEN	156+-3	113+-3	245-17
FABRIC SEMI-BLEACHED	OBR.1534	09C2-IIP	150-2	100	-	-	-	9,52 LINEN	9,52 LINEN	142+-3	112+-3	265 - 19
FABRIC SEMI-NATURAL	OBR.482	3C154-IIP +K+Y	150-2	100	-	-	-	9,09 LINEN	9,09 LINEN	142+-3	102+-3	280 - 20
FABRIC NATURAL	OBR.1237	05C304-IIP	150-2	100	-	-	-	9,09 LINEN	9,09 LINEN	142+-3	100+-3	280 - 20
FABRIC SEMI- BLEACHED Twill WEAVE	OBR.1458	08C141-IIP	150-2	100	-	-	-	9,09 LINEN	9,09 LINEN	143+-3	120+-4	280 - 20
FABRIC SEMI-NATURAL Twill WEAVE	OBR.1459	08C129-IIP	150-2	100	-	-	-	9,09 LINEN	9,09 LINEN	142+-3	122+-4	300 - 21
FABRIC NATURAL Twill WEAVE DES.2	OBR.1555	09C162-IIP	150-2	100	-	-	-	9,09 LINEN	9,09 LINEN	142+-3	130+-4	310 - 22
FABRIC NATURAL Twill WEAVE	OBR.2029	14C415-IIP	150-2	100	-	-	-	9,09 LINEN	K9,09 LINEN	142+-3	134+-4	320-22
FABRIC SEMI-BLEACHED	OBR.298	02C34- IIP/PIH	160-3	58	42	-	-	34X1 COTT.	33,3 LINEN	134+-3	135+-4	80 - 6
FABRIC SEMI-BLEACHED	OBR.0131	09C471- IIP/PIH	150-2	52	48	-	-	34X1 COTT.	33,3 LINEN	158+-3	132+-4	85 - 6
FABRIC SEMI-NATURAL	OBR.011	02C106- IIP/PIH	150-2	52	48	-	-	34X1 COTT.	33,3 LINEN	158+-3	132+-4	90 - 6

Fax: (372) 6839384
 Phone: (372) 6839383
 www.belinor.eu
 E-mail: info@belinor.eu

Minimum lot for dyeing fabrics in 1 color is 500-700 meters.
 The linen yarns Nm 9,52; 11,5; 17,2 are combed yarns.

SPECIFICATION ON THE PRODUCTS OF ORSHA LINEN MILL

DESCRIPTION	ARTICLE		WIDTH IN CMS	COMPOSITION OF FABRIC, %				COUNT OF YARN (METRIC)		DENSITY PER 10 CMS		WEIGHT OF 1 SQ. MTR. IN GRMS.	
	OLD	NEW		LINEN	COTT.	PE	VISC.	WARP	WEFT	WARP	WEFT		
FABRIC SEMI-BLEACHED	OBR.236	00C34- IIP/PIH	150-2	48	52	-	-	34X1 COTT.	33,3 LINEN	226+-5	176+-5	120 - 6	
FABRIC SEMI-NATURAL	OBR.026	03C124- IIP/PIH	150-2	49	51	-	-	34X1 COTT.	33,3 LINEN	226+-5	179+-5	125 - 6	
FABRIC SEMI-BLEACHED	OBR.045	05C273- IIP/PIH	150-2	57	43	-	-	34X1 COTT.	26,3 LINEN	226+-5	186+-6	140 - 10	
FABRIC SEMI-NATURAL	OBR.053	06C113- IIP/PIH	150-2	58	42	-	-	34X1 COTT.	26,3 LINEN	226+-5	196+-6	145 - 10	
FABRIC SEMI-BLEACHED	OBR.1634	10C179- IIP/PIH+Y	150-2	65	35	-	-	34X1 COTT.	20,0 LINEN	193+-4	160+-5	145 - 10	
FABRIC SEMI-BLEACHED	OBR.0207	13C493-IIP	150-2	53	47	-	-	20X1 COTT.	23,8 LINEN	179+-4	186+-6	170 - 13	
FABRIC SEMI-BLEACHED	OBR.1300	06C226- IIP/PIH	150-2	54	46	-	-	20X1 COTT.	17,9 LINEN	178+-4	144+-4	175 - 13	
FABRIC SEMI-NATURAL	OBR.0249	15C295- IIP+K	155-2	54	46	-	-	20X1 COTT.	17,9 LINEN	172+-4	148+-4	175 - 10	
FABRIC SEMI-BLEACHED	OBR.1773	10C816-IIP +Y	165-3	46	54	-	-	20X1 COTT.	20,0 LINEN	196+-4	152+-4	180 - 13	
FABRIC SEMI-NATURAL	OBR.1012	02C3-IIP+Y	150-2	58	42	-	-	20X1 COTT.	9,09 LINEN	176+-4	104+-3	210 - 15	
FABRIC SEMI-BLEACHED	OBR.1530	09C320-IIP	150-2	58	42	-	-	20X1 COTT.	9,52 LINEN	180+-4	104+-3	210 - 15	
FABRIC SEMI-BLEACHED TWILL 2/1	OBR.1759	10C788-IIP	153-2,5	58	42	-	-	20X1 COTT.	9,52 LINEN	208+-5	120+-3	225 - 16	

Fax: (372) 6839384
 Phone: (372) 6839383
 www.belinor.eu
 E-mail: info@belinor.eu

Minimum lot for dyeing fabrics in 1 color is 500-700 meters.
 The linen yarns Nm 9.52; 11,5; 17,2 are combed yarns.

SPECIFICATION ON THE PRODUCTS OF ORSHA LINEN MILL

DESCRIPTION	ARTICLE		WIDTH	COMPOSITION OF FABRIC, %				COUNT OF YARN (METRIC)		DENSITY PER 10 CMS		WEIGHT OF 1 SQ. MTR.	
	OLD	NEW	IN CMS	LINEN	COTT.	PE	VISC.	WARP	WEFT	WARP	WEFT	IN GRMS.	
FABRIC SEMI-NATURAL TWILL 2/1	OBR.1753	10C808-III	153-2,5	59	41	-	-	20X1 COTT.	9,09 LINEN	208+-5	126+-3	250 - 17	

Fax: (372) 6839384
 Phone: (372) 6839383
 www.belinor.eu
 E-mail: info@belinor.eu

Minimum lot for dyeing fabrics in 1 color is 500-700 meters.
 The linen yarns Nm 9,52; 11,5; 17,2 are combed yarns.